

TplusT, s.r.o.
A.Kmet' a 28
03601 Martin
Slovak republic
Tel +421 905 330250,905330251
Fax +421 43 4221615
Email: tplusT@gaya.sk

GLASS MAKING SANDS CLASS III/IV

Application: in glass-making industry for production glass, bodys and glace.

The size analysis

Sieve mesh diameter	Class III	Class IV
mm	%	%
> 1,0	0	0
> 0,5	3	3
0,1 - 0,5	94	94
< 0,1	3	3

The chemical constitution

parameters	Class III %	Class IV %
SiO₂	99,709	99,643
Fe₂O₃	0,022	0,031
TiO₂	0,033	0,060
Al₂O₃	0,039	0,068

The presented data are mean averages and depend on resource and production. We can give some information about tolerance limits of the chemical composition and the size analysis and about application the individual products. Our company gives free samples for testing. We realize delivery on the basis of negotiate sales conditions.