

TplusT, s.r.o.
A.Kmet' a 28
03601 Martin
Slovak republic
Tel +421 905 330250,905330251
Fax +421 43 4221615
Email: tplusT@gaya.sk

SILICA FLOUR M - 0,25/M - 0,075

Application: for production paints, paint mortar, adhesives and cleaners

Name	Fraction mm
Silica flour M – 0,25	0 – 0,25
Silica flour M – 0,075	0 – 0,075

The sieve analysis

Silica Flour M – 0,25

Sieve mesh diameter	Minus mesh limits
mm	%
0,50	100
0,25	90-100

Silica flour M – 0,075

Sieve mesh diameter	Minus mesh limits
mm	%
0,125	100
0,075	90-100

Silica flour M – 0,25

Silica flour M – 0,075

SiO₂	Fe₂O₃	SiO₂	Fe₂O₃
98,5%	0,15%	99,1%	0,031%

The presented data are mean averages and depend on resource and production. We can give some information about tolerance limits of the chemical composition and the size analysis and about application the individual products. Our company gives free samples for testing. We realize delivery on the basis of negotiate sales conditions.